



Trevor Boundy <trevor@boundy39.com>

FW: 104 Scaled Up 1/2A Fubar 600 - Clear Dope Coatings (Part 2)

1 message

Tandy Walker <rdb435021@icloud.com>
To: Trevor Boundy <trevor@boundy39.com>

Sat, Apr 20, 2019 at 5:11 AM

From: Tandy Walker [mailto:aerotan1503@outlook.com]
Sent: Tuesday, August 23, 2016 4:34 PM
Subject: 104 Scaled Up 1/2A Fubar 600 - Clear Dope Coatings (Part 2)

Scaled Up 1/2A Fubar 600

August 23, 2016

This afternoon I finished putting on seven (7) coats of clear dope as shown in Column (4) the table below.

Date: 8/23/16	Col (1)	Col (2)	Col (3)	Col (4)
Model Component	Clear Dope 50T/50D	Clear Dope 60T/40D	Tinted Dope 60T/40D	Total Dope Coats
Fuselage	1	1	5	7
Cowl	1	1	5	7
Rudder	1	1	5	7
Hatch - 1	1	1	5	7
Hatch - 2	1	1	5	7

This picture of the cowl shows the shiny finish after seven coats.



Here is another picture of the rear of the pylon after seven coats. The model will be set aside for 4 or 5 days to let the doped finish dry out some more. Then one final coat of clear satin Klass Kote will be sprayed on to complete the smooth satin finish.....Tandy



